

TECHNICAL DATA SHEET

PERLATO SICILIA COFANO®

Primary name	Perlato Sicilia Cofano®
Type of stone	Marble
Country of origin	Italy
Quarry location	Monte Cofano, Trapani (TP) - Sicily
Geological formation	Cretaceous
Color range	Beige
Description	Beige background with light brown fossil residues and light ivory 'pearls'
Average Block size	250 x 120 x 120 cm
Average Fabricated Slab size	250 x 120 cm
Available in Thin Tile	Yes
Maximum Thin Tile size	61 x 61 x 1 cm

TECHNICAL INFORMATION	ENGLISH VALUE	ASTM ** Test Method
Absorption by weight, %	0.20	C97
Density, lbs/ft ³ , (kg/m ³)	168	C97
Compressive strenght, psi, (MPa)	18,374	C170
Modulus of Rupture, psi, (MPa)	1074	C99
Abrasion resistance, hardness	1032	C880
Flexural strength, psi, (MPa) (Marble Only)	2,706	C241

MIA Classification for Soundness C (Marble Only)

Other trade names /

Color plate and information supplied by: Marmi e Graniti d'Italia Sicilmarmi Spa, Massa, Italy

Technical details provide a frame of reference only. Because stone is a product of nature, testing to determine specific physical should be repeated for each major project.

Control Number II - 01

** American Society for Testing and Materials; standards developed by Committee C18

© Copyright 1993, DIMENSION STONES OF THE WORLD © - Volume II; Marble Institute of America printed in U.S.A